

		Al	Ba	Ca	Fe	Mg	Mn	Si	Sr	Ti	C- total
		Wt %	Wt %	Wt %	Wt %	Wt %	Wt %	Wt %	Wt %	Wt %	Wt %
MAG 1 Standard	Average (n = 4)	7.3	0.04	1.0	4.2	1.5	0.07	20.7	0.01	0.35	2.3
	Std Dev (n = 4)	0.8	0.00	0.1	0.5	0.2	0.01	1.7	0.00	0.03	0.0
	Certified Values*	8.7	0.05	1.0	4.9	1.9	0.08	23.4	0.02	0.43	2.1

* <http://onlinelibrary.wiley.com/doi/10.1111/j.1751-908X.1981.tb00304.x/abstract>